


Curekind TCY(F)

DESCRIPTION	Items		Specification	
	 2,4,6-Trimercapto-s-triazine $C_3H_3N_3S_3$ M.W.:177.3 CAS No.: 638-16-4 EINECS No: 211-322-8	Appearance		Light-yellow powder
		Melting Point, °C	min.	320
		Heat Loss, %	max.	0.50
		Ash, % (800°C 2hr)	max.	0.30
		Density, g/cm ³		1.78
		Residue on 150µm, % max.		0.10
		Residue on 63µm, % max.		0.50

Characteristics Curekind® TCY is Light- yellow Powder. Melting Point and temperature of decomposition are above 320°C. Insoluble in water (20°C).

Application It is used for ACM,CO,ECO,CR and Rubber Blends. With fast vulcanizing speed, scorching safety, can be shorten the vulcanizing time, good mechanical properties for vulcanized rubber.

Safety and Toxic Refer to the MSDS.

Storage Store in closed containers in a cool, dry, well-ventilated place. Avoid exposure under direct sunlight.

Package Co-extruded paper bag lined with PE plastics film bag. N.W.25kg/bag; N.W.500kg/pallet.

The information contained in this leaflet is based on tests carried out by our laboratories and data selected from references. Therefore it is not valid legally and does not signify any guarantee to customers of successful applications of the product according to their own formulas. However, our company will offer professional services in technology at utmost to facilitate customers to achieve expected purpose of product applications.

Curekind®TCY(F) TECHNICAL DATA SHEET (TDS) version 1.3

Ningbo Actmix Polymer Co., Ltd.

TEL:+86-574-87576736 FAX:+86-574-88002102 Email:dychem@actmix.cn Http://www.actmix.cn/