

ACTMIX IS60-75GS

Vulcanizator Insoluble Sulfur IS60

A C T I V E M A T E R I A L	$[-S-]_n-$	PROPERTIES:	APPLICATIONS:	
	Insoluble sulfur	IS60 contains at least 60% of modified polysulfide insoluble in carbon disulfide and other similar solvents. It can be used as a vulcanizing agent to a variety of natural rubber, synthetic rubber. It leads to no blooming and no penetration to adjacent rubber layers and applies to storage, bonding between rubbers and rubber layers.	Industrial products such as tyres, conveyor belting, retreaded tyres, hoses, seals, rollers, etc	
	Molecular Formula: S _n			TYPICAL VALUES:
	M.W.: 32n			Sulfur content: Min 60.0%
	CAS: 7704-34-9		Ash content: Max 0.3%	
	EINECS: 231-722-6	DOSAGE:	Heating loss content: Max 0.5%	
		1-5phr, depending on different use and features.	150µm sieve residue: Max 0.5%	

M A S T E R B A T C H	PRODUCT	Active Content (%)	Appearance	Filtration (µm)	Binder	Sulfur Content (%)	Density (g/cm ³)	
	Actmix® IS60-75GS	75	Yellow Granules	-	SBR	74.0	1.37	
	* Binder type can be customized. Except SBR, others binders, such as NBR, EPDM/EVM also can be available for.							
	SAFETY&TOXICITY:							
	Please refer to related SDS.							
	PACKAGING&STORAGE:							
	Net weight 25kg/PE bags lined carton; Net 600 or 750 kg/pallet.							
	Shelf-life : 1 year in its original packaging							
	Stored in a dry and cool place.							

Compared to traditional IS60 powders, Actmix®IS60-75GS allows:

- Dust free products, guarantee of IS stability.
- Effective guarantee of activity of IS due to pre-dispersed masterbatch.
- Tack free products at room temperature, convenience and accuracy on ingredients.
- Lower Mooney viscosity at lower temperature (50°C), higher quality of dispersion.
- Impurity free, blocked filter free of extrusive products, scrap rate reduction and higher productivity thanks to filtration.
- Wider compatibility with other elastomers.

G: granule, P: plate, E: EPDM binder, N: NBR binder, S: SBR binder, A: ACM binder, EO: ECO binder.

The information contained in this leaflet is based on tests carried out by our laboratories and data selected from references. Therefore it is not valid legally and does not signify any guarantee to customers of successful applications of the product according to their own formulas. However, our company will offer professional services in technology at utmost to facilitate customers to achieve expected purpose of product applications.